

What is claimed is:

1. A poly(tetrafluoroethylene) polymer having:
- 5 (i) a melt flow index (372°C; 10kg) of at least 0.1 g/10 min;
- (ii) a strain at break at (25°C; 100/min) of at least 125%;
- (iii) a tensile strength (150°C; 100/min) of at least 7 MPa;
- (iv) a co-monomer content below 2.2 wt%;
- (v) a peak melting temperature above 315°C;
- 10 (vi) a crystallinity below 60%; and
- (vii) one or more of the following parameters:
- (a) a peak melting temperature below 320°C;
- (b) a crystallinity between 30% and 54%;
- (c) a melt-flow index (372°C/10kg) below 10g/10 min;
- 15 (d) a co-monomer content above 1 wt%.
2. The polymer of claim 1, wherein said polymer has a peak melting temperature in the range of above 315°C to below 320°C.
- 20 3. The polymer of claim 1, wherein said polymer has a crystallinity between 30% and 54%.
4. The polymer of claim 1, wherein said polymer has a melt-flow index (372°C/10kg) below 10g/10 min.
- 25 5. The polymer of claim 1, wherein said polymer has a co-monomer content above 1 wt%.
-
- sub
#16
- 30 6. The polymer according to any one of claims 1-5, wherein said polymer has two or more of said parameters (a)-(d).
7. The polymer according to any one of claims 1-5, wherein said polymer has

Sub
A1
cont

three or more of said parameters (a)-(d).

8. The polymer of claim 1, wherein said polymer has all four of said parameters (a)-(d).

5

Sub
A2

9. The polymer according to any one of claims 1-8, wherein said polymer has a melt flow index (372°C; 10kg) of at least 0.6 g/10min.

10 10. The polymer according to any one of claims 1-9, wherein said polymer has a strain at break at (25°C; 100/min) of at least 400%.

11. The polymer according to any one of claims 1-10, wherein said polymer has a tensile strength (150°C; 100/min) of at least 15 MPa.

15 12. The polymer according to any one of claims 1-11, wherein said polymer has a comonomer content between 1 and 1.4 wt%.

20 13. The polymer according to any one of claims 1-12, wherein said polymer has a peak melting temperature in the range of 316-319°C.

14. The polymer according to any one of claims 1-13, wherein said polymer has a crystallinity in the range of 35-44%.

25 15. The polymer according to any one of claims 1-13, wherein said polymer comprises a co-monomer selected from the group consisting of hexafluoropropylene, perfluoro(methyl vinyl ether), perfluoro(ethyl vinyl ether), perfluoro(propyl vinyl ether), perfluoro-(2,2-dimethyl-1,3-dioxole).

30 16. The polymer according to any one of claims 1-13, wherein said polymer comprises a perfluor(alkyl vinyl ether) co-monomer.

17. The polymer according to any one of claims 1-13, wherein said polymer comprises a perfluoro(propyl vinyl ether) co-monomer.

18. The polymer according to any one of claims 1-13, wherein said polymer comprises a hexafluoropropylene co-monomer.

19. A composition comprising the polymer according to any one of claims 1-18.

20. The composition of claim 19, wherein said composition comprises at least 20 wt% of said polymer.

21. The composition according to any one of claims 19-20, wherein said composition comprises at least 5 wt% of additives selected from the group consisting of colorants, fillers, reinforcing matter, blowing agents, foaming agents, and electrically conducting matter.

22. The composition according to any one of claims 19-21, wherein said composition comprises, titanium dioxide, carbon, graphite, glassfiber, molybdenum, bronze, or stainless steel.

23. A blend of two or more poly(tetrafluorethylene) polymers, at least one of said two or more poly(tetrafluorethylene) polymers being a polymer according to any one of claims 1-18.

24. An article comprising the polymer according to any one of claims 1-18.

25. The article of claim 24, wherein said article is formed at least in part by melt-processing said polymer.

26. A method comprising:
melt-processing the polymer according to any one of claims 1-18.

27. The method of claim 26, wherein said method includes injection molding, transfer-molding, melt-blowing, melt-extrusion, melt-spinning, and/or blow-molding.

5 28. An article obtained by the method of claim 27.

10098613.03.1802